

TECHNICAL DATA SHEET  
**My-T-Therm® 300 TCG**  
Thermally Conductive Grease  
January 2020



METLOK PRIVATE LIMITED  
(An ISO 9001 Certified Company)  
W-27, M.I.D.C. Industrial Area  
Kalmeshwar – 441 501, Nagpur

### Product Description

My-T-Therm® 300 TCG is a non-curing thermal interface material designed to transfer thermal energy from a heat source to a heat sink. This product delivers high thermal conductivity and electrical resistance over wide temperature range.

### Applications:

Typical applications include bonding

- ❖ Processor chips
- ❖ CPU, Transistor thermal modules and other heat generating electronic components to printed circuit board assemblies or heat sinks.

### Properties

My-T-Therm® 300 TCG provides the following product characteristics:

|  |                      |
|--|----------------------|
| Technology   | : Silicone Grease    |
| Components   | : One component      |
| Appearance   | : Grey paste         |
| Specific Gravity @ 25 °C   | : 2.75±0.03          |
| Viscosity Brookfield DV II+ Pro @ 25±2 °C; Spindle#7 Speed 20 r.p.m. ASTM D 1084 | : 60000-70000 cP     |
| Thermal Conductivity, ISO 22007  | : 3 W/(m-K)          |
| Service temperature  | : -50 °C to 200 °C   |
| Application  | : Thermal management |

### Directions for use

1. For best performance clean all surfaces (external and internal) with a cleaning solvent and allow drying. The assembled surfaces should be clean and free from dust dirt, oil and grease.
2. Apply My-T-Therm® 300 TCG to the desired surface and assemble the pieces.
3. Apply enough material to cover 100% area.

### Handling precautions

- ❖ For safe handling My-T-Therm® 300 TCG must be handled in a manner as indicated in Material Safety Data Sheet (MSDS) and in compliance with relevant local regulations.
- ❖ My-T-Therm® 300 TCG may affect certain plastics particularly thermoplastic materials or coatings. It is recommended to check all surfaces for compatibility before use.
- ❖ My-T-Therm® 300 TCG is non-volatile and non-flammable at room temperature.

### Storage

- ❖ Store Product My-T-Therm® 300 TCG in a cool, dry location in unopened containers at a temperature at 25±2 °C unless otherwise specified.
- ❖ Store away from sunlight and heat sources.
- ❖ My-T-Therm® 300 TCG will exhibit a shelf life of twelve months from the date of manufacturing when stored in above mentioned conditions.
- ❖ To prevent contamination of unused product, do not return any material to its original container. For further specific shelf life information, contact our technical service center R&D Center.

### Pack Size

My-T-Therm® 300 TCG is ideally available in 500gm and 1kg pack.

### Note

All statements, technical information and recommendations set forth herein are based on tests which Metlok Private Limited, believes to be reliable. However, Metlok Private Limited does not guarantee their accuracy or completeness. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against

any hazards that may be involved in the handling and use thereof. In no case will Metlok Private Limited be liable for direct, consequential economic or other damages.

\*\*\*\*\*

**METLOK PRIVATE LIMITED**

(Bonding and Sealing Solutions)

An ISO 9001: 2015 Certified Company

Tel.: 07118-271543/271170/272468

Fax: 07118-272470

Visit us at: [www.metlok.in](http://www.metlok.in)