

TECHNICAL DATA SHEET

My-T-Sil® 911

Acetoxy RTV Silicone

January 2019



METLOK PRIVATE LIMITED
(An ISO 9001 Certified Company)
W-27, M.I.D.C. Industrial Area
Kalmeshwar – 441 501, Nagpur

Product Description

My-T-Sil® 911 is a general industrial purpose, one-part, acetoxy cure, RTV Silicone sealant.

Product Feature:

- ❖ Low viscosity, Free flowing, self-leveling consistency
- ❖ Cures to a tough, rubbery substrate when exposed to moisture in the air.
- ❖ Excellent resistance to weathering, ozone, solar radiation, moisture, vibrations and many chemicals.
- ❖ Adheres to metals, plastics, ceramics, glass, non-oily wood, painted surfaces, concrete, natural & synthetic fibers, epoxies, silicones resins & rubber etc.

Product Characteristic

My-T-Sil® 911 provides the following product characteristics

Technology	: Silicone
Chemical type	: Acetoxy
Components	: One component
Appearance	: Liquid
Viscosity	: Low
Cure	: Room temperature vulcanizing (RTV)
Specific Benefit	: Adheres to a wide range of Substrates.

Applications:

- ❖ Bonding, Sealing, potting and Coating in electrical and electronic part.
- ❖ Suitable for Sealing assemblies with fine joints as well as cable entries
- ❖ Coating
 - Clean metal, plastic and glass
 - Flow coating over electric component
 - repair of industrial furnaces, ovens, boilers, exhaust stacks, high temperature ducting
- ❖ Potting
 - Electric equipment
 - Heating elements in electrical appliances

- ❖ Encapsulation
 - Securing delicate component in place

Properties

Colour	:	Red / White
Consistency	:	Self-leveling
Appearance	:	Liquid
Specific Gravity @ 25 °C	:	1.02
Viscosity, Brookfield 25±2 °C, DV II + Pro Spindle no. 6, Speed 2.5 r.p.m.	:	75000 to 125000 cP
ASTM D1084		
Service Temperature	:	- 65 to +200 °C

Cure Characteristics @ Room Temperature (25±2 °C) / 50±5 % RH

Skin Over Time	:	7-10 min.
Tack Free Time	:	30- 40min.
Cure Time [3mm thickness]	:	24 hrs.

Physical properties: 3 mm strip cure for 7 days @ 25±2 °C / 50±5% RH

Hardness, Durometer-Shore A, ASTM D 2240	:	20-30
Tensile Strength, ASTM D 412	:	≥ 0.5 N/mm ²
Elongation, ASTM D 412	:	200-300 %

Environmental Resistance

The product retains effective properties in contact with automotive fluids, such as motor oil, transmission fluids, antifreeze solutions and alcohol.

Directions for Use

1. For best performance bond surfaces should be clean and free from grease.
2. Remove excess sealant immediately with a cloth dampened with non-polar solvents.
3. Full properties will develop over 72 hrs.
4. Moisture curing begins immediately after the product is exposed to the atmosphere, therefore parts to be assembled should be mated within a few minutes after the product is dispensed.
5. Press or firmly clamp parts together. Do not slide parts together.

6. Excess cured material can be removed with a knife or sharp single edge razor blade. Avoid undercutting the seal.

Storage and Handling

- ❖ Store My-T-Sil® 911 in a cool, dry and unopened container.
- ❖ My-T-Sil® 911 will exhibit a shelf life of 6 months when stored as mentioned above.
- ❖ Storage information may be indicated on the product container labeling.
- ❖ Material removed from containers may be contaminated during use.
- ❖ Do not return product to the original container.
- ❖ Containers should always be kept sealed when not in use.
- ❖ If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Pack Size

My-T-Sil® 911 RTV silicone is ideally available in 100 ml tube, 280 ml cartridge and 20 Kg bucket/pail.

Note

All statements, technical information and recommendations set forth herein are based on tests which Metlok Private Limited, believes to be reliable. However, Metlok Private Limited does not guarantee their accuracy or completeness. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In no case will Metlok Private Limited be liable for direct, consequential economic or other damages.

METLOK PRIVATE LIMITED

(Bonding and Sealing Solutions)

An ISO 9001: 2015 Certified Company

Tel.: 07118-271543/271170/272468

Fax: 07118-272470

Visit us at: www.metlok.in